


SPECIFICATION FOR APPROVAL

1. Material

Production:	Sendust Cores
KDM.P/N:	KS068-026A-HF
AL:	19(nH/N ²) ± 8%
Material:	26 μ
Coating Color:	Black
Coating material:	epoxy
Coating Breakdown Voltage:	1000V, 0.5mA, 2Sec




2. Physical Characteristics

Before Coating			After Coating			Le(cm)	Ae(cm ²)	V(cm ³)	W(cm ²)	Weight (g) (ref.)	Box Quantity (Pieces)
OD(Max.) in/mm	ID(Min.) in/mm	Ht(Max.) in/mm	OD(Max.) mm	ID(Min.) mm	Ht(Max.) mm						
0.681 17.30	0.380 9.65	0.250 6.35	18.03	9.02	7.11	4.140	0.232	0.960	0.639	6.1	2400


3. Electrical Parameters(Typical) Temperature(25°C ± 2°C)

Test Item	Test Condition	Value(Typical)	Test Instrument
Inductance	φ 1.2mm/22Ts, 20kHz/1V, I=0A (Evenly full windings)(均匀绕满)	9.2 μ H ± 8%	CH3302
DC-Bias	φ 1.2mm/22Ts, 20kHz/1V, I=30A(H=200Oe) (Evenly full windings)(均匀绕满)	5.3 μ H (Min.)	WK3255B+WK3265B
	φ 1.2mm/22Ts, 20kHz/1V, I=45A(H=300Oe) (Evenly full windings)(均匀绕满)	3.7 μ H (Min.)	
Core Loss	50kHz/1000Gs	480mW/cm ³ (Max.)	SY-8219
Remarks	Set the internal resistance of LCR meter to 100 Ω .(电感测试仪内阻设置100 Ω)		

Core Loss Curves(Typical)



DC-Bias Curves(Typical)



KDM确认栏
KDM
Signature

**科达磁电
技术部**

客户确认栏
Customer
Signature

请在5个工作日内回签承认书，否则此承认书将作为后续订单的OQC标准。若有疑问，请及时联系我司RD部门。
Please sign back after approval within 5 working days, otherwise this approval sheet would be taken as OQC standard for subsequent orders. If you have any questions, please contact RD department in time.